





## Grade description

B10



<p><b>CTPK220</b> SILVERSTAR™</p>	<p>HC-K20</p>	
	<p><b>Specification:</b> Composition: Co 6.0%; mixed carbides 2.0%; WC balance   Grain size: 1 μm   Hardness: HV<sub>30</sub> 1630   Coating specification: PVD TiAlTaN</p> <p><b>Recommended application:</b> Optimal for the machining of high-tensile cast iron materials when toughness is required.</p>	
<p><b>CTWN215</b></p>	<p>HW-N15   HW-K15</p>	
	<p><b>Specification:</b> Composition: Co 6.0%; others 0.2%; WC balance   Grain size: submicron   Hardness: HV<sub>30</sub> 1650</p> <p><b>Recommended application:</b> The uncoated carbide grade for the machining of aluminium and other non-ferrous metals.</p>	