

# Technical information

## Material table



Material main group	Material sub-group	Quality	StNr	DIN	AFNOR	UNI	BS	JIS	SS	GOST	UNS	USA		
5 Cast steel	5.1 Conventional cast steel	5.1.2 low alloyed	1.6219	GS-22 MnNi 5										
			1.6221	GS-13 MnNi 6 4										
			1.6309	GS-20 MnMoNi 5 5										
			1.6511	GS-36 CrNiMo 4										
			1.6515	GS-25 CrNiMo 4										
			1.6552	GS-24 CrNiMo 3 2 5										
			1.6570	GS-30 NiCrMo 8 5										
			1.6582	GS-34 CrNiMo 6										
			1.6740	GS-33 NiCrMo 7 4 4										
			1.6741	GS-38 NiCrMo 8 4 4										
			1.6748	GS-40 NiCrMo 6 5 6										
			1.6750	GS-20 NiCrMo 3 7										
			1.6759	GS-18 NiMoCr 3 6										
			1.6760	GS-22 NiMoCr 5 6										
			1.6779	GS-14 NiCrMo 10 6										
			1.6781	GS-18 NiCrMo 12 6										
			1.6783	GS-19 NiCrMo 12 6										
			1.6916	GS-12 MnNiCrMo 5 3										
			1.7131	GS-16 MnCr 5										
			1.7147	GS-20 MnCr 5										
			1.7218	GS-25 CrMo 4										
			1.7219	GS-26 CrMo 4										
			1.7220	GS-34 CrMo 4										
			1.7225	GS-42 CrMo 4										
			1.7228	GS-50 CrMo 4										
			1.7341	GS-34 CrMo 4 4										
			1.7354	GS-22 CrMo 5 4										
			1.7354	GS-17 CrMnMo 5 5										
			1.7357	GS-17 CrMo 5 5										
			1.7363	GS-12 CrMo 19 5										
			1.7377	GS-17 CrMo 9 10										
			1.7379	GS-18 CrMo 9 10										
		1.7380	GS-12 CrMo 9 10											
		1.7382	GS-19 CrMo 9 10											
		1.7706	GS-17 CrMoV 5 11											
		1.7725	GS-30 CrMoV 6 4											
		1.7755	GS-35 CrMoV 10 4											
		1.7756	GS-36 CrMoV 10 4											
		1.7903	GS-18 MnCrMo 6 3											
		1.7906	GS-19 MnCrMo 6 3											
		1.7909	GS-20 MnCrMo 6 3											
		1.8159	GS-50 CrV 4											
				5.1.3 high alloyed	1.2201	G-X 165 CrV 12								
					1.2343	G-X 38 CrMoV 5 1	Z 38 CDV 5							
		1.2363	G-X 100 CrMoV 5 1		Z 100 CDV 5									
		1.2365	G-X 32 CrMoV 3 3		32 DCV 28									
		1.2367	G-X 40 CrMoV 5 3		Z 40 CDV 5									
		1.2392	G-X 28 CrMoV 5 1											
		1.2601	G-X 165 CrMoV 12											
		1.2606	G-X 37 CrMoW 5 1											
		1.2880	G-X 165 CrCoMo 12											
		1.3401	G-X 120 Mn 12		Z 120 M 12	XG 120 Mn 12	Z 120 M 12	SCMnH 1		110G13L		A 128 (A)		
		1.3966	G-X 25 MnCrNi 8 8 6											