







CTCP115	HC-P15 HC-K25 HC-M10	
	<p>Specification: Composition: Co 5.8%; mixed carbides 6.4%; WC balance Grain size: 1 - 2 μm Hardness: HV₃₀ 1550 Coating specification: CVD TiCN-Al₂O₃</p> <p>Recommended application: The wear-resistant high-performance grade for steel machining.</p>	

CTCP125	HC-P25 HC-K30 HC-M20	
	<p>Specification: Composition: Co 7.0%; mixed carbides 8.0%; WC balance Grain size: 1 - 2 μm Hardness: HV₃₀ 1450 Coating specification: CVD TiCN-Al₂O₃</p> <p>Recommended application: The first choice for the universal machining of steel.</p>	

CTCP135	HC-P35 HC-M25 HC-S25	
	<p>Specification: Composition: Co 9.6%; mixed carbides 6.7%; WC balance Grain size: 1 - 2 μm Hardness: HV₃₀ 1460 Coating specification: CVD TiCN-Al₂O₃ multi-layer</p> <p>Recommended application: The tough alternative for heavily interrupted cutting action.</p>	