






## Grade description

B10



<b>CTPK220</b> SILVERSTAR™	HC-K20	
	<p><b>Specification:</b> Composition: Co 6.0%; mixed carbides 2.0%; WC balance   Grain size: 1 μm   Hardness: HV<sub>30</sub> 1630   Coating specification: PVD TiAlTaN</p> <p><b>Recommended application:</b> Optimal for the machining of high-tensile cast iron materials when toughness is required.</p>	

<b>CTWN215</b>	HW-N15   HW-K15	 
	<p><b>Specification:</b> Composition: Co 6.0%; others 0.2%; WC balance   Grain size: submicron   Hardness: HV<sub>30</sub> 1650</p> <p><b>Recommended application:</b> The uncoated carbide grade for the machining of aluminium and other non-ferrous metals.</p>	