







<b>CTPP430</b>	HC-P30   HC-M25   HC-S25   HC-K30   HC-N25	
	<p><b>Specification:</b> Composition: Co 9.0%; others 0.75%; WC balance   Grain size: 0.85 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1590   Coating specification: PVD TiAlN</p> <p><b>Recommended application:</b> The universal high-performance grade for steel, austenitic steel and heat-resistant alloys.</p>	

<b>CTC1435</b>	HC-P35   HC-M30   HC-K20	
	<p><b>Specification:</b> Composition: Co 9.6%; mixed carbide 7.4%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1400   Coating specification: CVD TiCN-Al<sub>2</sub>O<sub>3</sub> multi-layer</p> <p><b>Recommended application:</b> First choice for steel and cast iron materials.</p>	

<b>CTP2440</b>	HC-M35   HC-P40   HC-N25   HC-S30	
	<p><b>Specification:</b> Composition: Co 9.6%; mixed carbides 7.4%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1400   Coating specification: PVD TiAlN</p> <p><b>Recommended application:</b> First choice for stainless and steel materials under unstable conditions.</p>	