









<b>CTCP125</b> BLACKSTAR™	HC-P25   HC-K30   HC-M20	
	<p><b>Specification:</b> Composition: Co 7.0%; mixed carbides 8.0%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1450   Coating specification: CVD TiCN-Al<sub>2</sub>O<sub>3</sub></p> <p><b>Recommended application:</b> The first choice for the universal machining of steel.</p>	

<b>CTCP135</b> COLORSTAR™	HC-P35   HC-M25   HC-S25	
	<p><b>Specification:</b> Composition: Co 9.6%; mixed carbides 6.7%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1460   Coating specification: CVD TiCN-Al<sub>2</sub>O<sub>3</sub> multi-layer</p> <p><b>Recommended application:</b> The tough alternative for heavily interrupted cutting action.</p>	

<b>CTPM125</b> SILVERSTAR™	HC-M25   HC-P35   HC-S25	
	<p><b>Specification:</b> Composition: Co 9.6%; mixed carbides 7.8%; others 0.4%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1460   Coating specification: PVD TiAlTaN</p> <p><b>Recommended application:</b> The first choice for the machining of austenitic steels.</p>	

<b>CTC2135</b>	HC-M30   HC-P35   HC-S35	
	<p><b>Specification:</b> Composition: Co 9.6%; mixed carbides 7.4%; WC balance   Grain size: 1 - 2 <math>\mu\text{m}</math>   Hardness: HV<sub>30</sub> 1400   Coating specification: CVD TiCN-TiNB multi-layer</p> <p><b>Recommended application:</b> The turning grade for stainless applications.</p>	